DW-A62L TRUSTARC™


Flux cored wire

Features:
- Excellent impact value down to -60℃
- Excellent CTOD value down to -40℃

Classification: AWS A5.29 E91T1-Ni2M-J

Shielding gas: Ar-20%CO_2
Polarity: DCEP

Welding Positions:



Packaging data

ϕ mm	Spool	
1.2	12.5kg	15kg
Volume mm	300W, 110H, 300L	

Composition (all-weld metal mass%)

	Typical	Guaranty [a]
C	0.07	0.12
Si	0.30	0.80
Mn	1.38	1.50
P	0.008	0.030
S	0.009	0.030
Ni	2.13	1.75~2.75

Note: [a] Single values are maximum.

Welding parameters (A)

ϕ mm	1F, 1G, 2F	2G	3G uphill, 4G
1.2	150~300	150~280	150~250

All-weld Mechanical properties

	Typical	Guaranty
0.2%YS (MPa)	560	538min.
TS (MPa)	640	621~758
El on 4d (%)	27	17min.
IV -60℃ (J)	82	27min.

Approvals

ABS	5YQ500SA H5
LR	5Y50S, H5
DNV	ⅤY50MS (H5)